

## Thinky Application Datasheet 12

### Viscous Epoxy Process - Vacuumless Defoaming Parameter - 6 minutes, 2000rpm

Materials: 828 Epoxy  
Capacity: 2.5cc in EFD 3cc syringe  
*It's capable from 3cc to 10cc syringe.*  
Viscosity: 32,000cP  
THINKY Mixer: Vacuumless mixer ARE-250  
Adapter: **250AD-EFD-3x6** for 3cc  
(250AD-EFD-5x6 for 5cc syringe, 250AD-EFD-10x4 for 10cc syringe)

