

Thinky Application Datasheet 14

LED phosphor (YAG)

Process - Dispersion, Vacuum Defoaming

Parameter - 5minutes, 2000rpm, 5Torr

Materials: LED phosphor

Capacity: 20g (phosphor 10 Volume %)

Viscosity: Silicone = 10,000cP

THINKY Mixer: Vacuum mixer ARV-310 + Syringe Loader

Container : SEMCO 75cc Barrel, EFD 5 syringe

