

## Thinky Application Datasheet 16

### Talc into Viscous Silicone

Process - Dispersion, Defoaming

Parameter - 2000rpm, 1min

Materials: Talc into the Silicone

Capacity: 60g (30wt%)

Viscosity: 10,000cP (Estimated)

THINKY Mixer: Vacuumless mixer ARE-250

Container : Standard 250ml cup

