NOVAGARD® SILICONES

RTV 400-195 Specification Data

DESCRIPTION

Novagard[®] RTV 400-195 is a non-corrosive, single-component silicone sealant and/or adhesive. A non-flowable, paste product, RTV 400-195 provides fast tackfree times and high green strength.

APPLICATIONS

As it is a faster curing version of Novagard RTV 400-150, RTV 400-195 is ideal for applications that require quick cures and early green strength development. As an adhesive, RTV 400-195 out performs slower materials in multi-step assembly applications where the fast tack and early strength combine to hold the assembly together as the unit moves from station to station.

INSTALLATION

As with all single component materials, worklife and cure times of RTV 400-195 are dependent upon environmental conditions such as temperature, humidity and application thickness. Adhesion should be checked on small samples prior to full-scale production.

AVAILABILITY

Novagard[®] RTV 400-195 is available in 10.3 oz. cartridges, 5-gallon pails, and 55-gallon drums.

STORAGE

Novagard[®] RTV 400-195 has a shelf life of twelve (12) months from the date of manufacture, as indicated by the lot number, when stored in the original, unopened container at, or below, 75°F.

PRODUCT SPECIFICATIONS

Physical Property	Test Method	Performance Range
Appearance		Translucent paste
Viscosity	Brookfield #7 @ 10rpm	3500 - 8000 poises
Skin Over Time	3/8" @ 50%RH & 77 [°] F	4-7 minutes
Through Cure	3/8" @ 50%RH & 77 [°] F	24 hours

PRECAUTIONS

Consult and obey all applicable local, state and federal regulations for disposal of solvent and silicone waste. For additional information consult product M.S.D.S.

Do not use in or around highly oxidative chemicals such as liquid oxygen, chlorine or peroxides. Not recommended for surfaces that are to be painted.

ADDITIONAL INFORMATION

Novagard believes that the information provided is a true and accurate description of the typical characteristics of the aforementioned product; however, it is the responsibility of the individual user to thoroughly test the product in their specific application to determine performance, efficacy and safety.

TYPICAL PROPERTIES*

Test Method	Typical Value
	1.00 - 1.05
ASTM D412	150-180 psi
ASTM D412	500-600%
ASTM D 624	30-35 pli
ASTM D 2240	20 ± 5
ASTM D 903	12-15 pli 10-14 pli 12-15 pli
	ASTM D412 ASTM D412 ASTM D 624 ASTM D 2240

*The values outlined reflect testing that was conducted on laboratory prepared specimens, actual results may vary. The information provided in the above table is not intended for use in preparing specifications. Please consult manufacturer for additional information.

Novagard *Solutions*TM 5109 Hamilton Avenue Cleveland, OH 44114

Form Name 10-D2-RX4195

Phone: (216) 881-3890 Facsimile: (216) 881-6977

04-01-08

Effective Date

WWW.NOVAGARD.COM